

[Label for plastic bag holding copper powder]

COPPERCOAT Copper Powder

THIS PRODUCT IS A PART OF A THREE COMPONENT PRODUCT.
TO BE MIXED ONLY WITH THE RESIN AND HARDENER PACKAGES CONTAINED WITH IT.

For use as a general antifoulant for freshwater and marine vessels*.

For use as a materials preservative against organisms that cause odor, stains, discoloration, deterioration or corrosion on surfaces.

Active Ingredient (powder portion only):

Copper Powder	99.7%
Other Ingredients	<u>0.3%</u>
Total	100%

EPA Registration # 85396-1

EPA Establishment # 85968-GBR-001

85396-FL-001



DANGER / PELIGRO

KEEP OUT OF REACH OF CHILDREN

MANTENER FUERA DEL ALCANCE DE LOS NIÑOS

Bag Disposal: Nonrefillable container. Do not reuse or refill this container. Completely empty bag into mixing container. Then offer for recycling if available or dispose of empty bag in a sanitary landfill or by incineration, or, if allowed by the state and local authorities, by burning. If burned stay out of smoke.

Eliminación del envase: Recipiente no rellenable. No reutilice o rellene este recipiente.

Vacíe completamente la bolsa en el equipo de aplicación, y luego ofrézcala para el reciclaje si está disponible, o deseche la bolsa vacía en un área adecuada para desechos sanitarios o por la incineración, o si está permitido por las autoridades locales y estatales, por quemar. Si se quema, manténgase alejado del humo.

Directions For Use

Mix the entire contents of this only with the other portions of this product. Mix immediately prior to use. See foldout for additional directions for use and application instructions.

Manufactured for
Coppercoat USA
1403 S. Patrick Dr. Unit 15
Indian Harbour Beach, FL 32937
Phone: 321-514-9197

Net Weight 4.4 lbs (2 kg) ~

***Not for use on recreational vessels in CA**

***No usar en embarcaciones recreativas en CA**

COPPERCOAT ANTI-FOUL

COPPERCOAT Copper Powder must be mixed with the Resin and Hardener before use.

ABN: COPPERCOAT DEFENSE ANTI-BACTERIAL

[COPPERCOAT DEFENSE Copper Powder must be mixed with the Resin and Hardener before use.
For use as a Preservative and Bacteriostatic Agent for commercial and residential sites]

For use as a general anti-foulant for freshwater and marine vessels.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS

DANGER: Causes irreversible eye damage. Do not get in eyes, on skin or on clothing. Harmful if swallowed, absorbed through skin or inhaled. Avoid breathing spray dust. Wear protective eyewear (goggles, face shield or safety glasses), rubber gloves, and a mask or pesticide respirator jointly approved by National Institute of Occupational Safety and Health when handling. Wash thoroughly with soap and water after handling and before eating, drinking, chewing gum, using tobacco or using the toilet. Remove and wash contaminated clothing before reuse.

DECLARACIONES DE PRECAUCIÓN RIESGOS PARA LOS SERES HUMANOS Y ANIMALES DOMÉSTICOS

PELIGRO: Causa daño ocular irreversible. No permita que caiga en los ojos, la piel o la ropa. Nocivo si se ingiere, se absorbe por la piel o se inhala. Evite inhalar el polvo del spray. Use gafas de protección (gafas de seguridad, careta o lentes de seguridad), guantes de caucho y una mascarilla o respirador para pesticidas aprobado conjuntamente por el Instituto Nacional de Seguridad y Salud Ocupacional al manipularlo. Lávese con abundante agua y jabón luego de manipular los pesticidas y antes de comer, beber, masticar chicle, usar tabacco, o ir al baño. Quítese y lave la ropa contaminada antes de reutilizarla.

FIRST AID PRIMEROS AUXILIOS	
IF IN EYES:	- Hold eye open and rinse slowly and gently with water for 15-20 minutes. - Remove contact lenses, if present, after the first five minutes, then continue rinsing eye. - Call a poison control center or doctor for treatment advice.
SI ENTRA EN CONTACTO CON LOS OJOS:	- Mantenga el ojo abierto y enjuáguelo lenta y cuidadosamente con agua, durante 15 a 20 minutos. - Si utiliza lentes de contacto, retirelos después de los primeros 5 minutos, luego continúe enjuagando {el ojo/los ojos}. - Llame al centro de control de envenenamientos o a un médico para consejo de tratamiento.
IF ON SKIN OR CLOTHING:	- Take off contaminated clothing. - Rinse skin immediately with plenty of water for 15-20 minutes. - Call a poison control center or doctor for treatment advice.
Si está en la piel o en la ropa:	- Quítese la ropa contaminada. - Enjuague la piel inmediatamente con bastante agua por 15-20 minutos. - Llame al centro de control de envenenamientos o a un médico para consejo de tratamiento.
IF INHALED:	- Move person to fresh air. - If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth, if possible. - Call a poison control center or doctor for further treatment advice.
Si es inhalado	- Traslade a la persona a un lugar con aire fresco. - Si la persona no está respirando, llame al 911 o a una ambulancia inmediatamente. Luego proceda a dar respiración artificial, preferiblemente de boca a boca, si es posible. - Llame al centro de control de envenenamientos o a un médico para consejo de tratamiento.
IF SWALLOWED:	- Call a poison control center or doctor immediately for treatment advice. - Have person sip a glass of water if able to swallow - Do not induce vomiting unless told to do so by a poison control center or doctor. - Do not give anything by mouth to an unconscious person.
Si se ingiere:	- Llame inmediatamente a un centro de control de envenenamientos o a un médico para consejo de tratamiento. - Si la persona puede tragar, haga que tome pequeños sorbos de agua. - No induzca el vómito a menos que así se lo indique un centro de control de envenenamientos o un médico. - No administre nada por vía oral a una persona inconsciente.

**HOT LINE NUMBER
NÚMERO DE LINEA DIRECTA**

Have the product container or label with you when calling a poison control center or doctor, or going for treatment. You may also contact 1-800-548-0489 for emergency medical treatment information.

Cuando llame a un centro de control de envenenamientos, o a un medico, o intente tratamiento, tenga a la mano el envase o la etiqueta del product. Para más informacion sobre el tratamiento médico de emergencia, También puede comunicarse al 1-800-548-0489.

ENVIRONMENTAL HAZARDS

Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans, and other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent into sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PELIGROS AMBIENTALES

Este product es tóxico para los peces y organismos acuáticos. No descargue los efluentes que contengan este product en lagos, arroyos, estanques, estuaries, océanos u otras aguas a menos que sea de acuerdo con los requisitos de un permiso del Sistema Nacional de Eliminación de Descargas de Contaminantes (NPDES, por sus siglas en inglés) y la autoridad otorgante haya sido notificada por escrito antes de la descarga. No descargue efluentes que contengan este product a los sistemas de alcantarillado sin notificar previamente a la autoridad local de la planta de tratamiento de aguas residuales. Para obtener orientación, comuníquese con la Junta Estatal de Agua o la Oficina Regional de la EPA.

Physical and Chemical Hazards

Warning: Do not breathe dust or fumes. Use only with adequate ventilation. Collect any spilled powder in a manner that minimizes further dust generation. Wear a NIOSH approved particle mask.

Peligros Físicos y Químicos

AVISO: Usar solo con ventilación adecuada. Recoge cualquier polvo derramado de una manera que minimice la generación adicional de polvo. Utilice un respirador para polvos y partículas aprobado por NIOSH que esté equipado con un filtro purificador.

STORAGE AND DISPOSAL / ALMACENAMIENTO Y DESECHO

Do not contaminate water, food or feed by storage and disposal.

No contamine agua, comida, ni forrajes mediant el almacenamiento o desecho.

PESTICIDE STORAGE: Store Powder in original container inside a dry area, -20°C to 40°C (0° to 100°F). Powder will oxidize, do not leave container open. If spilled carefully collect with dustpan and broom to minimize powder from getting into the air. Wear a particle mask when collecting. Place spilled material in plastic bag and dispose of in an approved waste disposal facility.

ALMACENAMIENTO DE PESTICIDAS: Almacene el polvo en su envase original dentro de un área seca, a -20°C a 40°C (0° a 100°F). El polvo se oxidará, no deje el envase abierto. Si se derrama, recoja cuidadosamente con una escoba y recogedor para minimizar que el polvo se disperse en el aire. Use una mascarilla para partículas al recogerlo. Coloque el material derramado en una bolsa de plástico y deséchelo en una instalación de eliminación de desechos aprobada.

PESTICIDE DISPOSAL: Waste resulting from the use of this product must be disposed of on site or at an approved waste disposal facility.

DESECHO DE PESTICIDAS: Los desechos resultantes del uso de este producto deben ser eliminados en el lugar o en una instalación de eliminación de residuos aprobada.

CONTAINER DISPOSAL: Nonrefillable container. Do not reuse or refill this container. Then offer for recycling if available or dispose of empty bag in a sanitary landfill or by incineration, or, if allowed by the state and local authorities, by burning. If burned stay out of smoke.

ELIMINACION DEL ENVASE: Recipiente no rellenable. No reutilice o rellene este recipiente. Luego ofrézcalo para reciclaje si está disponible o deseche la bolsa vacía en un vertedero sanitario o mediante incineración, o, si lo permiten las autoridades estatales y locales, mediante quema. Si se quema, manténgase alejado del humo.

Directions For Use/ Instrucciones de Uso

It is a violation of Federal Law to use this product in a manner inconsistent with it's labeling.

Es una violación de la ley federal utilizar este product de manera inconsistente con lo indicado en su etiqueta.

This product is not for use on recreational vessels in CA

*No usar en embarcaciones recreativas en CA

COPPERCOAT MULTI-SEASON PERFORMANCE ANTI-FOULING

FOR THE SUCCESSFUL APPLICATION OF COPPERCOAT MAKE SURE TO READ AND FOLLOW THESE INSTRUCTIONS CAREFULLY

[Revision: Published February 10, 2022]

Coppercoat anti-fouling is based on a water miscible epoxy resin, which is heavily loaded with pure grade (99%) fine copper powder .

Surface Preparation:

Fiberglass: As is common with all epoxy coatings, it is important that the substrate to be coated is well prepared. All surfaces must be cleaned of all contaminants, including dirt, dust, grease, rust or loose paint. Two-part epoxy coatings, such as Coppercoat, must be applied to sound and permanent substrates -consequently all surfaces must be cleaned of any previously applied single-part paint coatings or conventional anti-fouling. The best way to achieve this is sand or soda blasting, or with a non-toxic chemical paint remover. Finally, the hull must be sanded with 80 grit sandpaper to provide a good profile for the new epoxy coating. Remove the sanding dust before proceeding with the Coppercoat application -using either a soft brush or cloth. The hull can be washed with fresh water, making sure the surface is dry before proceeding. Under no circumstances should you clean the hull with any solvents or oil-based products (such as Acetone or MEK).

Fiberglass, gelcoat epoxy: After sanding the hull (and removing the dust) Coppercoat can be applied, or if desired, an epoxy barrier coating may be applied first.

Iron, Steel, Aluminum, Ferro-cement, Wood: All can be successfully coated with Coppercoat. However, once these substrates have been sanded and cleaned, they must be coated with the appropriate epoxy barrier coat before proceeding with the Coppercoat application. Full instructions can be obtained from CoppercoatUSA, as well as appropriate epoxy barrier coatings, if desired.

Mixing:

Mix Coppercoat one kit at a time. Coppercoat is supplied in three parts; Pack A (resin), Pack B (hardener), and a bag of fine copper powder. Mix Pack A with Pack B in an appropriately sized plastic mixing pot, then mix in Isopropyl Alcohol (91-99%) thinner, if using, and then continue to mix while carefully adding the copper powder. Stir until all the parts are mixed together, with all the copper suspended in the epoxy; don't over mix.

Note: While in the mixing pot, the copper may settle to the bottom of the mixing pot; stir the mixture occasionally to suspend the copper. A NIOSH approved particle mask must be worn while mixing the copper onto the epoxy.

Pot Life:

The average mixed pot life of Coppercoat is 30 minutes at 80 degrees Fahrenheit. Never mix more product than can easily be applied within the time available. Mix one kit of Coppercoat at a time.

Thinning:

Coppercoat should only be thinned with Isopropyl alcohol 91-99%. Under normal circumstances, Coppercoat may be thinned (if necessary) by 5% for application by roller. Up to 10% thinner may be added for application by spray. Refer to Coppercoat USA detailed instructions for additional information.

Environmental Conditions:

Do not attempt to apply Coppercoat if the ambient or hull temperatures are below 48 degrees Fahrenheit. With the epoxy being water miscible until cured, protect the hull from moisture for 48 hours.

Application:

The product should always be applied directly after mixing. Do not attempt to apply Coppercoat by brush. For application by roller, short pile 1/8" inch foam rollers for epoxy should be used (but not light duty cardboard-backed foam rollers). Coppercoat can also be applied by conventional spray - please contact Coppercoat USA LLC for fuller details. Note: We often use the term "tacky" in these instructions; the definition of "tacky" is when the Coppercoat has cured enough that it does not come off on your finger if you touch it; it may still be soft enough to push your fingernail into it.

Under normal circumstances, Coppercoat is applied in four thin coats, wet-on-tacky. Second, third and fourth coats should be applied as soon as the previous coat allows, -i.e. when the previous coat is tacky which is generally after approximately 30 minutes at 72 degrees Fahrenheit. The cure rate will be faster in warmer conditions and slower when it's cool. To ensure a satisfactory chemical bond between coats, all the required coats should be applied consecutively in a single day.

If the vessel to be treated is too large to be painted with all four coats in one day by the workforce available, paint a manageable sized section - apply all four coats to this section from start to finish in one day, before proceeding with a further section at a later time. If any product is left over after four coats have been applied continue the application until it is all used - this will ensure that the correct thickness of copper is present. Never attempt to apply a coat too thickly as this will result in sagging and runs.

Sanding:

It is necessary to sand the entire Coppercoat surface with 320 grit sandpaper to expose copper prior to launching. Although it takes 5 days for Coppercoat to fully cure, the coating will usually be cured enough to sand after 2-3 days; and it will be much easier to sand at that time. If the coating "gums up" the sandpaper, wait a little longer before continuing. We recommend that a dust mask (at a minimum) be worn while sanding the Coppercoat.

Coverage Rate

The effective coverage rate for a finished application is 42 square feet per 1.5 litre kit. Therefore, a hull that is 420 square feet will need 10 kits of Coppercoat in total.

Shelf Life:

Coppercoat is generally good for 12 months in the original sealed containers at 68 degrees Fahrenheit. Shelf life will be shortened if stored in warmer conditions. Keep protected from frost. If the copper powder is stored, seal it in an additional plastic sealing bag; any moisture will make the copper hard and unusable.

Tool Cleaning:

If the epoxy has not yet cured equipment can be cleaned in water. Do not use white spirit, naphtha or methylated spirits.

Maintenance:

Damaged areas can be touched up as required. Occasional cleaning to remove slime and prevent soft growth accumulation is generally required; depending on water temperature, salinity and other factors, some areas require more or less cleaning. Most people clean the hull with a piece of carpet or a squeegee or brush.

Precautions/ Precauciones:

Follow usual good hygiene practices and wash skin free of any product immediately, before it cures, using soap and warm water. Any splashes to the eyes should be washed immediately with plenty of clean water and medical advice sought. Read the hazard labels.

Siga las prácticas de higiene habituales y lave la piel inmediatamente con agua tibia y jabón para eliminar cualquier resto de producto, antes de que seque. En caso de contacto con los ojos, lávelos inmediatamente con abundante agua limpia y consulte a un médico. Lea las etiquetas de advertencia.

If you are in any doubt over the use or application of Coppercoat, please contact **Coppercoat USA LLC at 1-321-514-9197** for further advice and information.

Manufactured for Coppercoat USA
1403 S. Patrick Dr., Unit 15
Indian Harbour Beach, FL 32937
Phone: 321-514-9197

EPA Registration #85396-1
EPA Establishment # 85968-GBR-001
85396-FL-001

Feb. 28, 2022

Directions For Use as a Materials Preservative/ Instrucciones de Uso Como Conservante de Materiales

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

Es una violación de la ley federal utilizar este producto de manera inconsistente con lo indicado en su etiqueta.

Coppercoat Defense Anti-bacterial is a roller applied or spray-on preservative and bacteriostatic agent which inhibits the growth of mold, mildew, fungus and bacteria that cause odor, discoloration, staining, deterioration or corrosion of the coated surfaces. Coppercoat Defense Anti-bacterial also prevents slime mold accumulation on treated surfaces. It is a three-part system consisting of copper powder, a resin and a hardener applied on the surface and providing residual protections. Coppercoat can be used to protect any nonfood contact surface made of metal, ceramic, tile, fiberglass, plastic, wood and wallboard.

This product is for nonfood contact surfaces only. This product is anti-bacterial for organisms that cause odor, stains, discoloration, deterioration or corrosion on surfaces.

No product treated with this product may make any public health claims relating to antibacterial activity without first obtaining an EPA registration for the product which permits such claims. No claim is made that this product protects users of any products listed below against food borne or disease-causing bacteria, viruses, germs or other disease-causing organisms.

COPPERCOAT DEFENSE ANTI-BACTERIAL COATING

FOR THE SUCCESSFUL APPLICATION OF COPPERCOAT DEFENSE ANTI-BACTERIAL COATING ON NON-EMERSION SURFACES READ AND FOLLOW THESE INSTRUCTIONS CAREFULLY

[Revision: Published February 28, 2022]

Coppercoat Defense Anti-Bacterial Coating is based on a water miscible epoxy resin, which is heavily loaded with pure grade (99%) fine copper powder.

Surface Preparation, Non-emersion: As with all epoxy coatings, it is important that the substrate to be coated is well prepared. All surfaces must be cleaned of all contaminants, including dirt, dust, grease, rust or loose paint. Two-part epoxy coatings, such as Coppercoat Defense, must be applied to sound and permanent substrates - consequently all surfaces must be cleaned of any previously applied single-part paint. Under no circumstances should you clean the surface with any solvents or oil-based products (such as Acetone or MEK).

Iron, Steel, Aluminum, ceramics, tile, wallboard, plastic, fiberglass and wood can be coated with Coppercoat Defense with proper surface preparation. Some surfaces will benefit from a coat of Coppercoat epoxy without the copper prior to applying the Coppercoat; review the following instructions for the substrate/surface to be coated.

Note: We often use the term "tacky" in these instructions; the definition of "tacky" is when the Coppercoat has cured/dried enough that it does not come off on your finger if you touch it; it can still be soft enough to push your fingernail into it.

Metal Surface Applications

1. Steel: For application to steel surfaces in non-emersion service, make sure surface is clean and that no single part paints are on the surface; if so, remove them. The surface should be sanded with 40-60 grit sandpaper; remove all sanding dust before applying the Coppercoat Defense to the surface with a roller in 3 to 4 thin coats, wet-on-tacky, all in one day.
2. Stainless Steel: For application to stainless steel in non-emersion service, make sure the surface is clean and no single part paints are on the surface; if so, remove them. The surface needs to be sandblasted with black beauty or similar type of blast media, leaving a minimum of a 2-mil anchor profile. If unable to blast, use a MBX Bristol Blaster with SS tines, leaving a 2-mil anchor profile. Clean the surface before applying a tack-coat of Coppercoat epoxy without the copper, and then apply 3 to 4 coats of Coppercoat Defense to the surface wet-on-tacky, all in the same day.
3. Aluminum: For application to aluminum in non-emersion service, make sure the surface is clean and no single part paints are on the surface; if so, remove them. The surface needs to be sanded with 40-60 grit sandpaper; remove all sanding dust before applying the Coppercoat resin without copper in a thin coat, then apply 3 or 4 thin coats of Coppercoat Defense, all in one day, wet-on-tacky.

Non-Metal Surface Applications

1. Ceramics and Tile: For application to ceramic tile make sure the surface is clean and no single part paints are on the surface; if so, remove them. The surface needs to be sanded well with 40-60 grit sandpaper; remove all sanding dust before applying 3 or 4 thin coats of Coppercoat Defense, all in one day, wet-on-tacky.
2. Fiberglass and Plastic: For application to fiberglass and plastic make sure the surface is clean and no single part paints are on the surface; if so, remove them. The surface needs to be sanded well with 80 grit sandpaper and then remove all sanding dust before applying 3 or 4 thin coats of Coppercoat Defense, wet-on-tacky, all in one day.
3. Wood: For application of wood the surface must be clean and free of any single part paint. Sand the surface with 80 grit sandpaper and remove all sanding dust before applying 3 or 4 thin coats of Coppercoat Defense, wet-on-tacky, all in one day.
4. Wallboard: Make sure the surface is clean. The surface needs to be sanded well with 80 grit sandpaper and then remove any sanding dust before applying 3 or 4 thin coats of Coppercoat Defense on the surface, wet-on-tacky, all in one day.

Mixing:

Mix Coppercoat Defense one kit at a time, and unless you are coating a large surface, mix partial batches - see Partial Mixing, below. A kit of Coppercoat Defense consists of three parts:

Pack A (resin), Pack B (hardener), and a bag of fine copper powder. Mix Pack A with Pack B in an appropriately sized plastic container, then continue to mix while carefully adding the copper powder. Stir until all the parts are mixed together, with all the copper suspended in the epoxy, but don't overmix. Note: While in the mixing pot, the copper may settle to the bottom of the mixing pot; stir the mixture occasionally to suspend the copper. A NIOSH approved particle mask must be worn while mixing the copper into the epoxy.

Partial Mixing:

It is often necessary to mix partial batches of Coppercoat Defense when the surface to be coated is less than 42 square feet or the workforce is less than 3 people. The mixing ratio is "1-part Resin, to 1-part Hardener, to .8-parts Copper powder".

Pot Life:

The average mixed pot life of Coppercoat Defense is 30 minutes at 80 degrees F. Never mix more product than can easily be applied within the time available.

Thinning:

Coppercoat Defense should only be thinned with Isopropyl Alcohol 91-99%. Under normal circumstances, Coppercoat may be thinned (if necessary) by 5% for application by roller. Up to 10% thinner may be added for application by spray.

Environmental Conditions:

Do not attempt to apply Coppercoat Defense if the ambient or surface temperatures are below 48 degrees Fahrenheit. With the epoxy being water miscible until cured, protect the surface of the new Coppercoat Defense from all moisture for 48 hours or it will wash away.

Application:

The product should always be applied directly after mixing. Do not attempt to apply Coppercoat Defense by brush. For application by roller, 1/8" inch foam rollers for epoxy should be used (but not light duty cardboard-backed foam rollers). Coppercoat Defense can also be applied by conventional spray - please contact Coppercoat USA LLC for details.

Coppercoat Defense should be rolled on in four very thin coats. Second, third and fourth coats should be applied wet-on-tacky as soon as the previous coat allows - i.e. after approximately 30 minutes at 72 degrees Fahrenheit. To ensure a satisfactory chemical bond between coats, all the required coats should be applied consecutively in a single day.

On many projects, by the time the first coat has been completed, the start point is cured enough to apply the second coat, so the application of the Coppercoat Defense Coating is continuous. The cure rate will be faster in warmer conditions and slower in cooler conditions; if the Coppercoat Defense is still wet enough to come off on your finger or lifts when you roll on another coat, wait a little longer.

If the area to be treated is too large to be painted with all coats in one day by the workforce available, simply coat a manageable sized section - apply all the necessary coats to this section from start to finish in one day, before proceeding with a further section at a later date. Always apply Coppercoat Defense in very thin coats; do not apply a coat too thickly, as this will result in sagging and runs and a rough surface.

Sanding:

After curing for 2-3 days sand the entire surface with 320 grit sandpaper to expose copper. Although it takes 5 days for Coppercoat Defense to fully cure, the coating will usually be cured enough to sand after 2-3 days; and it will be much easier to sand at that time. If the coating "gums up" the sandpaper, wait a little longer before continuing. A dust mask (at a minimum,) should be worn while sanding the Coppercoat Defense.)

Coverage Rate:

The coverage rate for a finished application of Coppercoat Defense is 42 square feet, per 1.5 litre kit. Therefore, a surface area of 420 square feet in area will need 10 kits of Coppercoat Defense Anti-Bacterial Coating.

Shelf Life:

12 months in sealed containers at 68 degrees Fahrenheit. Shelf life will be shortened if stored in warmer conditions. Keep protected from frost. If copper powder is stored, seal it in additional plastic sealing bags; any moisture will make the copper hard and unusable.

Tool Cleaning:

If the epoxy has not yet cured, equipment can be cleaned with water.

Do not use white spirit, naphtha or methylated spirits.

Maintenance:

Damaged areas can be touched up as required. Sand the area to be touched up with 80 grit sandpaper and apply more Coppercoat Defense Coating to that area in the same manner as described above for applications.

If you have questions about the use or application of Coppercoat Defense Anti-bacterial Coating, please contact **Coppercoat USA LLC at 1-321-514-9197** for further advice and information.

Manufactured for

Coppercoat USA

1403 S. Patrick Dr, Unit 15

Indian Harbour Beach, FL 32937

Phone: 321-514-9197

EPA Registration # 85396-1

EPA Establishment # 85968-GBR-001

85396-FL-001

Feb 28, 2022